

PRODUCT CODE: M880SA	COMMERCIAL NAME: ACRILFOND TX 1881 E
DESCRIPTION	Two-components acrylic transparent non yellowing sealer

PROPERTIES	
Recommended for / Main area of application	Two-components acrylic non-yellowing sealer with UV filters, with good rapidity and sanding properties. Suitable to paint light-coloured woods, such as ash wood. Suggested to do kitchens, furniture for interior and furnishing in general.
Application Method	By spraygun, airless, by curtain coater
Shelf life	24 months

APPLICATION PROPERTIES		PHISICAL PROPERTIES	
Quantity	120 - 150 gr/mq	Viscosity	32 " +/-4" DIN 4
Vertical Stability	-	Solid Content	21 +/- 3%
Cathalysis	B410SA 10%	Specific Weight	0.915 +/-0,020 Kg/Lt
Dilution	P730SA 20%	Glossy	-
Pot Life	> 4 h	Ph	-

GENERAL INFORMATION			
Drying at 20°C		Oven Drying	
Dust Free	10'	Time for Flash Off	-
Touch Free	30'		
Sanding	3 h	Time for drying	-
Overcoating	6 h		
Stackable	6 h	Time for cooling	-

RECOMMENDED APPLICATION PROCESS	
On a raw wood apply 2 coats, 30 - 40 minutes from one another, of M880SA - ACRILFOND TX 1881 E catalysed at 10% with B410SA - CAT. B 41 and thinned at 20% with P730SA - DILUENTE POL. EXTRA.	
After at least 3 hours sand with sand paper 240 - 400 and apply a coat of an acrylic matt topcoat, suggested serie M150...SA - OBI 150 VARI GLOSS.	

ALTERNATIVE HARDENERS		PERFORMANCES
B420	10%	More adhesion and resistance to scratches.
-	-	-
-	-	-

ALTERNATIVE THINNER
-

NOTES	User is responsible to make the application of the product in a place with an adequate air-recycle and on respecting of all hygienic and safety regulations.
--------------	--

STORAGE	Containers must be stored tightly closed in a well-ventilated place with temperatures between 5° C and 35°C.
----------------	--