

PRODUCT CODE: G920SA	COMMERCIAL NAME: VF A 892
DESCRIPTION	Two-components polyurethanic transparent sealer

PROPERTIES	
Recommended for / Main area of application	Two-components polyurethanic transparent sealer, widely consumed, with good covering and sanding properties that make it suitable for many productions. Suggested for furniture and accessories for interior.
Application Method	By spraygun and by curtain coater
Shelf life	24 mesi

APPLICATION PROPERTIES		PHISICAL PROPERTIES	
Quantity	130 - 150 gr/mq	Viscosity	43" +/-4" DIN 4
Vertical Stability	-	Solid Content	43 +/- 3%
Cathalysis	B400SA 50%	Specific Weight	0.977 +/-0,020 Kg/Lt
Dilution	P730SA 30%	Glossy	-
Pot Life	> 3 h	Ph	-

GENERAL INFORMATION			
Drying at 20°C		Oven Drying	
Dust Free	15'	Time for Flash Off	-
Touch Free	30' - 40'		
Sanding	3 - 4 h	Time for drying	-
Overcoating	12 h		
Stackable	4 h	Time for cooling	-

RECOMMENDED APPLICATION PROCESS	
Apply a coat of a stain, suggested C520..SA - UNICOLOR SERIE. After 30 minutes apply by spraygun 130 - 150 gr/mq of G920 - VF A 892 catalysed at 50% with B400SA - CAT. B 40 and thinned at 30% with P730SA - DILUENTE POL. EXTRA. After 40 - 60 minutes apply a sec ond coat of G920SA - VF A 892 as above explained. After 8 - 12 hours sand with sand paper 220 - 400 and apply a coat of a polyurethanic topcoat, suggested H410...SA - VPK 744 VARI GLOSS.	

ALTERNATIVE HARDENERS		PERFORMANCES
B370SA	50%	-
B540SA	50%	More filling properties
-	-	-

ALTERNATIVE THINNER
-

NOTES	User is responsible to make the application of the product in a place with an adequate air-recycle and on respecting of all hygienic and safety regulations.
--------------	--

STORAGE	Containers must be stored tightly closed in a well-ventilated place with temperatures between 5° C and 35°C.
----------------	--