TECHNICAL DATA SHEET

Release: 0

Date: 17/12/2025

PRODUCT CODE: H12005SA	**COMMERCIAL NAME:** VM 120 TX 5 GLOSS
DESCRIPTION	Two-components polyurethanic transparent topcoat

PROPERTIES	
Recommended for / Main area of application	Polyurethanic topcoat with excellent filling properties, excellent verticality and softness to the touch. Suggested for flat surfaces, asembled furniture and doors for interior.
Application Method	By spraygun, airless, by curtain coater
Shelf life	24 months

APPLICATION PROPERTIES		PHISICAL PROPERTIES	
Quantity	120 - 140 gr/mq	**Viscosity**	43 " +/-5" DIN 4
Vertical Stability	100 gr/mq	**Solid Content**	40 +/- 3%
Cathalysis	B400SA 50%	**Specific Weight**	0.969 +/-0,020 Kg/Lt
Dilution	P730SA 20%	**Glossy**	5 +/-2 G
Pot Life	> 3 h	**Ph**	-

GENERAL INFORMATION			
Drying at 20°C		**Oven Drying**	
Dust Free	10' - 15'	**Time for Flash Off**	-
Touch Free	60'		
Sanding	-	**Time for drying**	-
Overcoating	-		
Stackable	6 - 8 h	**Time for cooling**	-

RECOMMENDED APPLICATION PROCESS
Apply a coat of an universal stain, suggested serie C520SA - UNICOLOR SERIE. After 10 - 30 minutes apply two coats, 40 - 60 minutes from one another, of a polyurethanic transparent sealer, suggested G850SA - VF A 143. After 8 - 12 hours sand with sand pape r 240 - 400 and apply by spraygun 120 - 140 gr/mq of H12005SA - VM 120 TX 5 GLOSS, catalysed at 50% with B400SA - CAT. B 40 and thinned at 20% with P730SA - DILUENTE POL. EXTRA

ALTERNATIVE HARDENERS		PERFORMANCES
-	-	-
-	-	-
-	-	-

ALTERNATIVE THINNER
-

NOTES	User is responsible to make the application of the product in a place with an adequate air-recycle and on respecting of all hygienic and safety regulations.

STORAGE	Containers must be stored tightly closed in a well-ventilated place with temperatures between 5° C and 35°C.