

PRODUCT CODE: G300SA	COMMERCIAL NAME: VF BIANCO 300
DESCRIPTION	Two-components polyurethanic white sealer

PROPERTIES	
Recommended for / Main area of application	Two-components polyurethanic white sealer with excellent filling properties, excellent covering properties and good sanding properties. It is also suitable to be overpainted with polyurethanic glossy varnishes. Suggested to do bathroom furniture, kitchens, wardrobes, doors for interior. Suitable for MDF and for every kind of wood.
Application Method	By spraygun, airless, by curtain coater
Shelf life	24 mesi

APPLICATION PROPERTIES		PHISICAL PROPERTIES	
Quantity	180 - 220 gr/mq	Viscosity	42 " +/-5" DIN 8
Vertical Stability	-	Solid Content	73 +/- 3%
Cathalysis	B400SA 30% by weight and 50% by volume	Specific Weight	1.450 +/-0,050 Kg/Lt
Dilution	P730SA 20% by weight and 30% by volume	Glossy	-
Pot Life	> 3 h	Ph	-

GENERAL INFORMATION			
Drying at 20°C		Oven Drying	
Dust Free	10'	Time for Flash Off	-
Touch Free	60'		
Sanding	3 - 4 h	Time for drying	-
Overcoating	8 - 12 h		
Stackable	6 h	Time for cooling	-

RECOMMENDED APPLICATION PROCESS
Apply by spraygun 180 - 220 gr/mq of G300SA - VF BIANCO 300, catalysed at 30% by weight with B400SA - CAT. B 40 and thinned at 20% by weight with P730SA - DILUENTE POL. EXTRA.
After 40 - 60 minutes, apply a second coat of G300SA - VF BIANCO 300, as above explained.
The following day sand with sand paper 220 - 400 and apply a coat of a polyurethanic white topcoat, suggested serie H360...SA - VPK BIANCO 260 VARI GLOSS.

ALTERNATIVE HARDENERS		PERFORMANCES
B540	30% by weight and 50% by volume	It increases the covering properties
B180	50% by weight and 70% by volume	It increases the pot life (suggested during summer)
B510	30% by weight and 50% by volume	It increases the pot life (suggested during summer); it gives more elasticity to the product

ALTERNATIVE THINNER
P030SA 30% by weight and 50% by volume

NOTES	User is responsible to apply the product in a place with an adequate air-recycle and to respect all hygienic and safety regulations.
--------------	--



TECHNICAL DATA SHEET

Release: 6

Date: 27/11/2018

STORAGE	Containers must be stored tightly closed in a well-ventilated place with temperatures between 5°C and 35°C.
---------	---