

PRODUCT CODE: WAC0SA	COMMERCIAL NAME: IDROFOND 6776 TX INT
DESCRIPTION	Monocomponent water-based transparent sealer for interior

PROPERTIES	
Recommended for / Main area of application	Monocomponent water-based transparent sealer for interior, with high trasparency , high covering and good restoration of the wood . Suggested for all kind of wood (conifers and broad-leaved woods).
Application Method	By spray
Shelf life	12 months

APPLICATION PROPERTIES		PHISICAL PROPERTIES	
Quantity	100-200 gr/mq	Viscosity	15000 +/- 4000 cps (rpm5) Brookfield SP4
Vertical Stability	-	Solid Content	31 +/-2 %
Cathalysis	-	Specific Weight	1.030 +/-0,030 Kg/Lt
Dilution	Deionised Water 0 - 5%	Glossy	-
Pot Life	-	Ph	-

GENERAL INFORMATION			
Drying at 20°C		Oven Drying	
Dust Free	30'	Time for Flash Off	-
Touch Free	1 h	Time for drying	-
Sanding	4 h		
Overcoating	6 h		
Stackable	24 h	Time for cooling	-

RECOMMENDED APPLICATION PROCESS
On a raw support apply by spraygun 100 -200 gr/mq of WAC0SA IDROFOND 6776 TX INT, as it is or thinned up to 5% with deionised water. After 3 - 4 hours, sand with abrasive paper with grain 240 - 320 and apply a second coat of WAC0SA - IDROFOND 6776 TX INT, as above explained. For a higher covering , waiting 6 - 8 hours , sand with abrasive paper with grain 240 - 320 and apply a third coat

ALTERNATIVE HARDENERS	PERFORMANCES
-	-
-	-
-	-

ALTERNATIVE THINNER
-

NOTES	User is responsible to apply the product in a place with an adequate air-recycle and to respect all hygienic and safety regulations.
--------------	--

STORAGE	Don't keep product in a place with temperature < 5°C (it does not stand cold) and > 35°C. The drying of water-based products must take place in suitable and well ventilated places (temperature > 15°C and relative humidity < 85%).
----------------	---