

|                               |                                                         |
|-------------------------------|---------------------------------------------------------|
| <b>PRODUCT CODE:</b> WAD015SA | <b>COMMERCIAL NAME:</b> CONVERTER IDRO BIANCO INT 15 GL |
| <b>DESCRIPTION</b>            | Monocomponent white water-based converter               |

| PROPERTIES                                        |                                                                                                                                                                                                                                                                                                 |
|---------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Recommended for / Main area of application</b> | Monocomponent white water based converter to apply on support with water based sealer suitable for the application for all kind of furniture .<br>The product is a converter for strong colours, that can be pigmented up to 15% with water-based pastas from our serie R900 - P.C. IDRO SERIE. |
| <b>Application Method</b>                         | By spraygun, airless, airmix                                                                                                                                                                                                                                                                    |
| <b>Shelf life</b>                                 | 12 months                                                                                                                                                                                                                                                                                       |

| APPLICATION PROPERTIES    |                        | PHISICAL PROPERTIES    |                      |
|---------------------------|------------------------|------------------------|----------------------|
| <b>Quantity</b>           | 120-140 gr/mq          | <b>Viscosity</b>       | " +/-6" VN           |
| <b>Vertical Stability</b> | -                      | <b>Solid Content</b>   | 36 +/- 3%            |
| <b>Cathalysis</b>         | -                      | <b>Specific Weight</b> | 1,020 +/-0,020 Kg/Lt |
| <b>Dilution</b>           | Deionised water 0 - 5% | <b>Glossy</b>          | 15 +/-3 G            |
| <b>Pot Life</b>           | -                      | <b>Ph</b>              | -                    |

| GENERAL INFORMATION |      |                           |   |
|---------------------|------|---------------------------|---|
| Drying at 20°C      |      | Oven Drying               |   |
| <b>Dust Free</b>    | 30'  | <b>Time for Flash Off</b> | - |
| <b>Touch Free</b>   | 1 h  | <b>Time for drying</b>    | - |
| <b>Sanding</b>      | -    |                           |   |
| <b>Overcoating</b>  | 12 h |                           |   |
| <b>Stackable</b>    | 24 h | <b>Time for cooling</b>   | - |

| RECOMMENDED APPLICATION PROCESS                                                                                                                                                                                                                                                                                                                       |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Apply two coats of a water-based sealer, suggested WAA0SA- IDROFOND 6771 BIANCO INT<br>After having sanded the substrate, apply by spraygun 130 gr/mq of WAD015SA - CONVERTER IDRO BIANCO 6777 INT 15 GLOSS, pigmented up to 5 - 6% with water-based pigment ed pastas from our serie R900 - P.C. IDRO SERIE, thinned at 0 - 5% with deionised water. |

| ALTERNATIVE HARDENERS | PERFORMANCES |
|-----------------------|--------------|
| -                     | -            |
| -                     | -            |
| -                     | -            |

| ALTERNATIVE THINNER |
|---------------------|
| -                   |

|              |                                                                                                                                                                                                                         |
|--------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>NOTES</b> | User is responsible to apply the product in a place with an adequate air-recycle and to respect all hygienic and safety regulations. After having catalysed it, mix well and let it rest for 5 minutes before using it. |
|--------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

|                |                                                                                                                                                                                                                                       |
|----------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>STORAGE</b> | Don't keep product in a place with temperature < 5°C (it does not stand cold) and > 35°C. The drying of water-based products must take place in suitable and well ventilated places (temperature > 15°C and relative humidity < 85%). |
|----------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|