

PRODUCT CODE: TAA0SA	COMMERCIAL NAME: HF FONDO IDRO X EST
DESCRIPTION	Fondo all'acqua per esterno.

PROPERTIES	
Recommended for / Main area of application	Outdoor water bottom, recommended for window frames, balconies, and doors. Can be used on ekumé and softwoods.
Application Method	Spray , airless
Shelf life	12 months

APPLICATION PROPERTIES		PHISICAL PROPERTIES	
Quantity	-	Viscosity	" -
Vertical Stability	-	Solid Content	27 +/-2 %
Cathalysis	-	Specific Weight	1.040 +/-0,050 Kg/Lt
Dilution	0-5% ACQUA	Glossy	-
Pot Life	-	Ph	-

GENERAL INFORMATION			
Drying at 20°C		Oven Drying	
Dust Free	90'-120'	Time for Flash Off	-
Touch Free	120'-150'		
Sanding	16-24 hours	Time for drying	-
Overcoating	16-24 hours		
Stackable	24 hours	Time for cooling	-

RECOMMENDED APPLICATION PROCESS
Apply a coat of impregnant to spray or flow-coating wood. After at least 2/4 hours spray apply _____ - HF BOTTOM HYDRO XEST diluted with water up to a maximum of 5%. After 16/24 sand and spray apply a coat of water-based finish.

ALTERNATIVE HARDENERS	PERFORMANCES
-	-
-	-
-	-

ALTERNATIVE THINNER
-

NOTES	It is the user's specific responsibility to ensure that the application takes place in an adequately ventilated environment and in compliance with hygiene and safety regulations.
--------------	--

STORAGE	Store in tightly closed containers in a ventilated place and with temperatures between 5°C and 35°C.
----------------	--